

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

## **TEST REPORT**

Client : Delta Panel 2828 Ipswic Darra QLD	h Road	Test Number Issue Date Print Date	: 21-00353 : 20/07/202 : 20/07/202	21
Sample Description	Clients Ref : "DeltaCorroCorro-TPC" Insulated building panel End Use : Insulated Building Panel Nominal Composition : Pre-painted stee Core Nominal Mass per Unit Area/Density : Nominal Thickness : 100mm	l skins bonded to Thermosettir 34kg/m3	ng Phenolic Com	posite
S/NZS 1530.3-1999	Methods for Fire Tests on Building Materi Part 3: Simultaneous Determination of Igr Flame Propagation, Heat Release and Sm	itability,	ires	
	Face tested:	Face (Alternate)		
	Date tested:	20-07-2021		
		Standard Error	Mean	
	Ignition time	Nil	Nil	min
	Flame propagation time	Nil	Nil	sec
	Heat release integral	Nil	Nil	kJ/m²
	Smoke release, log d	0.1258	-1.3184	
	Optical density, d		0.0582	/ metre
	Number of specimens ignited:		0	
	Number of specimens tested:		6	
	Regulatory Indices:			
	Ignitability Index		0	
	Spread of Flame Index		0	Range 0-10
	Heat Evolved Index		0	Range 0-10
	Smoke Developed Index		3	Range 0-10

243168

52882

C Australian Wool Testing Authority Ltd Copyright - All Rights Reserved Accredited for compliance with ISO/IEC 17025 - Testing



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

12



Page 1 of 2





A



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

## **TEST REPORT**

Client : Delta Panels Pty Ltd 2828 Ipswich Road Darra QLD 4076

Test Number	:	21-003532
Issue Date	:	20/07/2021
Print Date	:	20/07/2021

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

Ignition is initiated by a pilot flame that is held near, but does not touch the specimen. A material that does not ignite during the standard test may ignite if contacted with a pilot flame during the test.

Each test specimen had an unattached backing of 4.5mm thick fibre reinforced cement board.

Each test specimen was clamped in four places.

243168

52882

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

12

Fiona McDonald APPROVED SIGNATORY





MICHAEL A. JACKSON B.Sc.(Hons)

C